



		Max	Min
Residual Induction Br	G	7,100	6,700
Coercive Force Hc	Oe	6,000	5,500
Intrinsic Coercive Force Hci	Oe	9,800	9,100
Max. Energy Product (BH)max	MGOe	11.0	10.0
Material Density	g/cm ³	5.8	
Max. Operating Temperature	C	120	
Temperature Coefficient for B	-%/C	0.11	
Temperature Coefficient for H	-%/C	0.39	
Required Magnetizing Force	Oe	20,000	
Material Composition	MQ Powder w/Epoxy		

Compression Molded NdFeB magnets are made with a patented NdFeB melt spun process and are compounded with an epoxy resin. The resulting magnets have a higher loading of magnet material and therefore stronger magnetic characteristics.

For more information please call or email Alliance technical support at:

Phone: **219-548-3799** Fax: **219-548-7071** email: **engineering@allianceorg.com**